

TECHNICAL DATA

GENERAL INFORMATION	TECHNICAL INFORMATION	TEST METHOD	APPLICATIONS
MATERIAL: BLACK ABSOLUTE	COMPRESSIVE STRENGTH:	3011 kb/cm ²	RESIDENTIAL <input checked="" type="checkbox"/>
MATERIAL TYPE: GRANITE	WATER ABSORPTION:	0.01%	LIGHT TRAFFIC <input checked="" type="checkbox"/>
ORIGIN: ZIMBABWE	BULK DENSITY:	2989 kg/m ³	HEAVY TRAFFIC <input checked="" type="checkbox"/>
QUARRY PRODUCTIVITY:	ULTIMATE TENSILE STRENGTH:	280 kg/cm ²	WET AREAS <input checked="" type="checkbox"/>
POOR <input type="checkbox"/>	COEFF. THERMAL EXPANSION:	0.0065 mm/mm ⁰ C	INDOOR FLOORING <input checked="" type="checkbox"/>
ADEQUATE <input type="checkbox"/>	FRICTIONAL WEAR:		OUTDOOR FLOORING <input checked="" type="checkbox"/>
GOOD <input checked="" type="checkbox"/>	IMPACT TEST/MIN. FALL HEIGHT:	69 cm	INDOOR COVERING (WALLS) <input checked="" type="checkbox"/>
EXCELLENT <input type="checkbox"/>	BENDING TENSILE STRENGTH:		OUTDOOR COVERING (WALLS) <input checked="" type="checkbox"/>
	AFTER FREEZING:	2636 kg/cm ²	INDOOR COUNTERTOP <input checked="" type="checkbox"/>
			OUTDOOR COUNTERTOP <input checked="" type="checkbox"/>
			SWIMMING POOL FLOORING AND COVERING <input checked="" type="checkbox"/>

Information provided by Marble Institute of America