

## TECHNICAL DATA

GENERAL INFORMATION	TECHNICAL INFORMATION	TEST METHOD	APPLICATIONS
<b>MATERIAL:</b> GREEN BOWENITE	<b>COMPRESSIVE STRENGTH:</b>	2607 kg/cm <sup>2</sup>	RESIDENTIAL <input checked="" type="checkbox"/>
<b>MATERIAL TYPE:</b> GRANITE	<b>WATER ABSORPTION:</b>	0.23%	COMMERCIAL <input checked="" type="checkbox"/>
<b>ORIGIN:</b> SOUTH AFRICA	<b>BULK DENSITY:</b>	2751 kg/m <sup>3</sup>	LIGHT TRAFFIC <input checked="" type="checkbox"/>
<b>QUARRY PRODUCTIVITY:</b>	<b>ULTIMATE TENSILE STRENGTH:</b>	134 kg/cm <sup>2</sup>	HEAVY TRAFFIC <input checked="" type="checkbox"/>
POOR <input type="checkbox"/>	<b>COEFF. THERMAL EXPANSION:</b>		WET AREAS <input checked="" type="checkbox"/>
ADEQUATE <input type="checkbox"/>	<b>FRICTIONAL WEAR:</b>		INDOOR FLOORING <input checked="" type="checkbox"/>
GOOD <input checked="" type="checkbox"/>	<b>IMPACT TEST/MIN. FALL HEIGHT:</b>	72 cm	OUTDOOR FLOORING <input checked="" type="checkbox"/>
EXCELLENT <input type="checkbox"/>	<b>AFTER FREEZING:</b>	1973 kg/cm <sup>2</sup>	INDOOR COVERING (WALLS) <input checked="" type="checkbox"/>
			OUTDOOR COVERING (WALLS) <input checked="" type="checkbox"/>
			INDOOR COUNTERTOP (VANITIES) <input checked="" type="checkbox"/>
			OUTDOOR COUNTERTOP <input checked="" type="checkbox"/>
			SWIMMING POOL FLOORING AND COVERING <input checked="" type="checkbox"/>